



filtraPAC® LV
POLIANIONIC CELLULOSE
LOW VISCOSITY HIGH QUALITY

GRADE	TECHNICAL
DEFINITION	WATER SOLUBLE ANIONIC POLYMER DERIVED FROM CELLULOSE
APPLICATION	SALT & FRESH WATER BASED DRILLING FLUIDS
NAME	FILTRA-PAC LV
USK REF NO	7014
CUSTOMER	ALERIS
LOT NO	550/1302
DATE	02.01.2016.
PRODUCT EXPIRY DATE	02.01.2018.
WEIGHT	10000 KG

ANALYSIS	RANGE	TEST METHOD	RESULTS
APPEARANCE	Free Flowing white powder	Visual check	PASS
MOISTURE %	Max. 10	ASTM	5.0
pH (%1)	6 - 8	ASTM	7.5
Bulk Density g/cm ³	Min 1,5	ASTM	1.6
Apparent viscosity (cPs)	Max 25	API SPEC RP13I	20
Fluid loss (ml)	Max 16	API SPEC RP13I	9.8
DS	Min 0.9	ASTM	10
Purity	Min 70%	ASTM	85%

CONCENTRATION : The recommended initial treatment for FILTRA-PAC LV is from 0.8 to 3.5 kg/m³ depending on the salt level, other solid content and water quality.

PACKING: Net 25 kg triple Kraft paper bags with polyethylene inner lining
HANDLING & STORAGE: USK brand PAC are not dangerous item for purposes of transport regulations. Bags should be stored cool and dry indoors.

UGUR SELULOZ-KIMIYA-MAKINA
ve GIDA SAN. ve TIC.A.Ş.
Organize Sanayi Bölgesi-Umurlu-AYDIN
Tel.: 0250.259 12 44
Gözelhisar Y.D. 116/003 0971



ISO 9001:2008